



**F. REPORTING OF RESULTS**

Report the amount of abrasion loss in grams. The age of the concrete shall be included in the report.

**G. SAFETY AND HEALTH**

Prior to handling, testing or disposing of any waste materials, testers are required to read: Part A (Section 5.0), Part B (Sections: 5.0, 6.0 and 10.0) and Part C (Section 1.0) of Caltrans Laboratory Safety Manual. Users of this method do so at their own risk.

**REFERENCES;**

End of Text (California Test 550 contains 3 pages)





FIGURE 1- MECHANICAL SHAKER



8	8	Ball Bearings	10.3 mm dia., 4.5 g, Steel		
1	7	Retaining Ring	4140 Steel		
2	6	"O" Ring	106.4 mm ID x 109.5 mm OD x 3.2 mm dia. Neoprene		
4	5	Cap Screws	10-32NF Socket, Filister HD		
1	4	Base	Alum		
1	3	Wear Plate	4140 Steel		
1	2	Cover	Alum		
1	1	Body	Mild Steel		
No. Req.	Part No.	Description	Stock Size	Material	Remarks

FIGURE 2- SURFACE ABRASION TEST MOLD