Revised RHMA-G Acceptance In Place

Quality characteristic	Test method	Requirement
Hamburg wheel track (min number of passes at	AASHTO T 324	
0.5-inch rut depth)	(Modified)	
Binder grade of base stock:		
PG 58		15,000 10,000
PG 64		20,000 15,000
PG 70		25,000 20,000
Hamburg wheel track (min number of passes at	AASHTO T 324	
inflection point)	(Modified)	
Binder grade:		
PG 58		10,000 Report Only
PG 64		12,500 Report Only
PG 70		15,000 Report Only

Revised RHMA-G Mix Design Requirements

Hamburg wheel track (min, number of passes at	AASHTO T 324	
•		
0.5-inch rut depth)	(Modified) ^d	
Binder grade base stock:		15,000 10,000
PG 58		20,000 15,000
PG 64		25,000 20,000
PG 70		
Hamburg wheel track (min, number of passes at	AASHTO T 324	
the inflection point)	(Modified)d	
Binder grade:		
PG 58		10,000 Report Only
PG 64		12,500 Report Only
PG 70		15,000 Report Only