

Summary of Changes:

CT 306, "Method of Test for Reducing Samples of Asphalt Mixtures to Testing Size"



Section	AASHTO R 47-19 (old)	CT 306 / AASHTO R 47-19 (new)
Overview	National Standard for reducing asphalt mixtures to testing size.	New test method CT 306 referenced in CT 125 Appendix B for asphalt mixture sample reduction to testing size. CT 306 references AASHTO R 47-19 to be used with non-rubberized asphalt mixtures and provides a second procedure for use with rubberized asphalt mixtures.
Procedure	Previously applied to both non-rubberized and rubberized asphalt mixtures.	<p>CT 125 requires sample sets of 4 boxes each.</p> <p>Non-rubberized asphalt mixtures: Reduce per AASHTO R 47-19.</p> <p>Rubberized asphalt mixtures: To obtain the necessary test sample weight, remove approximately equal portions from the front vertical face of each box within the sample set using a taping knife, scoop, and spatula.</p>