

Test ID Numbers for Performance Graded Modified (PG-M) Asphalt Binders

PRODUCT TYPE
PG 58-34 M
PG 64-28 M
PG 76-22 M

TEST ID	TEST METHOD	TEST NAME	UNIT	DECIMAL PLACES
40708	AASHTO T48	Flash Point	°C	0
40710	AASHTO T44	Solubility of Bituminous Material	%	1
40712	AASHTO T316	Rotational Viscosity	Pa·s	3
40714	AASHTO T315	G*/SinDelta on Original Binder	KPa	3
40716	AASHTO T240	Mass Change after RTFO, Plus or Minus	%	3
40718	AASHTO T301	Elastic Recovery	%	1
40720	AASHTO T315	G*/SinDelta on RTFO Residue	KPa	3
40722	AASHTO T315	Delta @ 2.2 KPa on RTFO Residue + 6°	Degrees	1
40724	AASHTO T315	G*SinDelta on Residue from PAV	KPa	1
40726	AASHTO T313	Creep Stiffness on Residue from PAV	MPa	1
40728	AASHTO T313	M-Value on Residue from PAV	Slope	3
40732	AASHTO T228	Specific Gravity	(none)	4